

TORNADO CONSTRUCTOR BLANCO



FAMILY
LINE

PAREDES Y TECHOS

MATE

DESCRIPTION AND NATURE

Highly efficient paint for walls and ceilings, ideal for low-demand areas or spaces requiring frequent repainting. Highly breathable.

USAGES

Indoors
Cement
Concrete
Brick
Drywall (gypsum plasterboard): fibreboard

PROPERTIES

Gloss level: matt (according to UNE-EN 13300, at 85° reflectance < 10)
High sweating
Washability: Class 4 (according to Standard UNE-EN 13300)
Opacity: Class 2 for a performance of 8 m²/litre (according to Standard UNE-EN 13300)

TECHNICAL CHARACTERISTICS

Referencia Color	TORNADO CONSTRUCTOR BLANCO
Finish	Matt
Specific weight	1,62 ± 0,05 kg/l
Viscosity	120 +/- 15 PO
Solids in volume	44 ± 1
Solids in weight	67 ± 1
VOC	Cat. a/BA 75/30 (2007/2010): 1,03 g/l
Aproximated performance by coat	8-10 m ² /L
Dry to touch	(20°C HR: 60%): 1 h. Washing: 25-30 days
Dry to repaint	(20°C HR: 60%): mín: 3-4 h. Máx: Without limit
Colours	White
Washability	CLASE 4

SURFACE PREPAIRING

New surfaces

Cement and concrete mortars:

1. Wait till complete drying of product (30 days minimum).
2. Remove off any efflorescences by abrasive jet
3. Neutralize alkaline surfaces.
4. Extremely polished surfaces should be sanpapered to open pores.
5. Remove off any foreign products or remains.
6. Bad condition surfaces should be anchored properly: Emulsión Fijadora or Fijamont.
7. Fill defects in the substrate (see family 6).

Plaster, plaster-covered brick:

1. Wait till complete drying of product (20% max. Moisture level).
2. Remove off any foreign product or product remains.
3. Remove off any efflorescences.
4. Use a sealant or matt paste to regulate surface absorption.

TORNADO CONSTRUCTOR BLANCO

5. Extremely polished surfaces should be sandpapered to open pore.
6. Very damaged surfaces should be fixed with suitable product: Emulsión Fijadora or Fijamont.
7. Cover surface imperfections with plaster or putty (See Family 6).

Plasterboard partition walls:

1. Carry out a general sanding of the joints and putty fixing areas.
2. Then, clean them to ensure the substrate is free of dust, grease and other contaminants.
3. For application on coloured boards that tend to generate stains, apply Montoplac Sellador Antimanchas.

Restoring and maintenance

1. Remove off old paint completely.
2. Brilliant surfaces should be matted to ensure good adherence.
3. Check paint type and anchoring in painted surfaces to avoid incompatibilities. Remove off any dust or dirt before painting.
4. Cover surface imperfections with suitable putty of plaste (Plasmont).
5. Mildewed surfaces should be treated with Monto Limpia Moho.

WAY OF USE

Application notes

- Shake product until perfectly homogenized.
- First coat should be diluted depending on surface condition and porosity level.
- Finish with one or more coats slightly diluted until surface is totally covered.
- Do not apply product at temperatures below 5°C or any surfaces which have been exposed to sunshine.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	5-10%
Air-less gun	5-30%
Aerographic gun	5-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Drywall (gypsum plasterboard)			
MAX	Fijamont o Emulsión fijadora	Tornado constructor	Tornado constructor
STD	Tornado constructor diluido		Tornado constructor
New work			
MAX	Fijamont o Emulsión fijadora	Tornado constructor	Tornado constructor
STD	Tornado constructor diluido		Tornado constructor
Old paintings			
MAX	Fijamont o Emulsión fijadora	Tornado constructor	Tornado constructor
STD	Tornado constructor diluido		Tornado constructor

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

TORNADO CONSTRUCTOR BLANCO

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

15 L



FAMILY LINE

DESCRIPTION AND NATURE

Highly efficient paint for walls and ceilings, ideal for low-demand areas or spaces requiring frequent repainting. Highly breathable.

USAGES

PROPERTIES

Gloss level: matt (according to UNE-EN 13300, at 85° reflectance < 10)

High sweating

Washability: Class 4 (according to Standard UNE-EN 13300)

Opacity: Class 2 for a performance of 8 m²/litre (according to Standard UNE-EN 13300)

TECHNICAL CHARACTERISTICS

Referencia Color

Finish Matt

Specific weight 1,62 ± 0,05 kg/l

Viscosity 120 +/- 15 PO

Solids in volume 44 ± 1

Solids in weight 67 ± 1

VOC Cat. a/BA 75/30 (2007/2010): 1,03 g/l

Aproximated performance by coat 8-10 m²/L

Dry to touch (20°C HR: 60%): 1 h. Washing: 25-30 days

Dry to repaint (20°C HR: 60%): mín: 3-4 h. Máx: Without limit

Colours White

Washability CLASE 4

SURFACE PREPAIRING

TORNADO CONSTRUCTOR BLANCO

New surfaces

Cement and concrete mortars:

1. Wait till complete drying of product (30 days minimum).
2. Remove off any efflorescences by abrasive jet
3. Neutralize alkaline surfaces.
4. Extremely polished surfaces should be sanpapered to open pores.
5. Remove off any foreing products or remains.
6. Bad condition surfaces should be anchored properly: Emulsión Fijadora or Fijamont.
7. Fill defects in the substrate (see family 6).

Plaster, plaster-covered brick:

1. Wait till complete drying of product (20% max. Moisture level).
2. Remove off any foreign product or product remains.
3. Remove off any efflorescences.
4. Use a sealant or matt paste to regulate surface absorption.
5. Extremely polished surfaces should be sandpapered to open pore.
6. Very damaged surfaces should be fixed with suitable product: Emulsión Fijadora or Fijamont.
7. Cover surface imperfections with plaster or putty (See Family 6).

Plasterboard partition walls:

1. Carry out a general sanding of the joints and putty fixing areas.
2. Then, clean them to ensure the substrate is free of dust, grease and other contaminants.
3. For application on coloured boards that tend to generate stains, apply Montoplac Sellador Antimanchas.

Restoring and maintenance

1. Remove off old paint completely.
2. Brilliant surfaces should be matted to ensure good adherence.
3. Check paint type and anchoring in painted surfaces to avoid incompatibilities. Remove off any dust or dirt before painting.
4. Cover surface imperfections with suitable putty of plaste (Plasmont).
5. Mildewed surfaces should be treated with Monto Limpia Moho.

WAY OF USE

Application notes

- Shake product until perfectly homogenized.
- First coat should be dilluted depending on surface conditon and porosity level.
- Finish with one or more coats slightly dilluted until surface is totally covered.
- Do not apply product at temperatures below 5°C or any surfaces which have been exposed to sunshine.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	5-10%
Air-less gun	5-30%
Aerographic gun	5-30%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Drywall (gypsum plasterboard)			
MAX	Fijamont o Emulsión fijadora	Tornado constructor	Tornado constructor
STD	Tornado constructor diluido		Tornado constructor
New work			
MAX	Fijamont o Emulsión fijadora	Tornado constructor	Tornado constructor
STD	Tornado constructor diluido		Tornado constructor

502770

Fecha de Alta

24-03-2026

Versión

2 - 16/09/2026

TORNADO CONSTRUCTOR BLANCO



Old paintings

MAX Fijamont o Emulsión fijadora

Tornado constructor

Tornado constructor

STD Tornado constructor diluido

Tornado constructor

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

PACKINGS

15 L