

Fecha de Alta

24-02-2026

Versión

2 - 24/03/2026 :



FAMILY PAREDES Y TECHOS / SISTEMAS TINTOMÉTRICOS
LINE MATE PREMIUM

DESCRIPTION AND NATURE

Special commemorative edition for the 65th anniversary of Pinturas Montó. Contains citral fragrances. High-performance paint for walls and ceilings with an excellent balance of resistance, application, coverage and performance.

USAGES

Indoors/Outdoors
 Walls and ceilings
 Cement mortars
 Concrete
 Brick
 Plaster
 Dripping effect
 Drywall (gypsum plasterboard): fibreboard

PROPERTIES

Minimum splattering (Tixoless Technology)
 Reaction to fire classification: A2 s1,d0 according to standard UNE-EN 13501-1
 Perfumed
 Washability: Class 1 (according to Standard UNE-EN 13300)
 Gloss level: extra matt (according to UNE-EN 13300, at 85° reflectance < 5)
 High coverage (UNE-EN ISO 6504-3): Class 1 (UNE-EN 13300) with a yield of 5-6 m²/l
 With anti-mould additive
 Gardner Washability Standard DIN 53778: 50.000 d.p

TECHNICAL CHARACTERISTICS

Referencia Color	OVALDINE 65 BLANCO
Specific weight	1,5± 0,05 kg/l
Viscosity	85 +/- 10 PO
Solids in volume	47± 1
Solids in weight	65± 1
VOC	Cat. a/BA 75/30 (2007/2010):2,44 g/l
Aproximated performance by coat	14-16 m ² /L

Dry to touch	(20°C HR:60%):1h
Dry to repaint	(20°C HR:60%):3-4h
Colours	White BL, IN, TR bases Tintometric System Colours.

SURFACE PREPARING

New surfaces

Cement and concrete mortars:

1. Wait until fully set (min. 30 days).
2. Clean any efflorescence with a jet washer.
3. Neutralize alkaline surfaces.
4. Sand polished surfaces to create a rougher surface.
5. Clean the surface to remove foreign products.
6. Set crumbly substrates with Emulsión Fijadora or Fijamont.

Fecha de Alta

24-02-2026

Versión

2 - 24/03/2026 :

7. Fill in defects in the substrate (see family 6).

Plaster, plaster-covered brick:

1. Wait until it is completely dry (max. 20% humidity).
2. Clean the surface to remove foreign products.
3. Clean any efflorescence with a jet washer.
4. Regulate surface absorption with sealer, fixer, or a diluted coat of the same product.
5. Sand polished surfaces to create a rougher surface.
6. Set crumbly substrates with Emulsión Fijadora or Fijamont.
7. Fill in defects in the substrate (see family 6).

Plasterboard partition walls:

1. Carry out a general sanding of the joints and putty fixing areas.
2. Then, clean them to ensure the substrate is free of dust, grease and other contaminants.
3. For application on coloured boards that tend to generate stains, apply Montoplac Sellador Antimanchas.

Restoring and maintenance

1. Completely remove old paint that is in poor condition or that is poorly-adhered.
2. Glossy surfaces should be thinned out to ensure good adhesion.
3. On painted surfaces, check that the paint is solid and well-adhered. Its condition must be assessed, in order to avoid possible incompatibilities. Dust and dirt must also be eliminated before repainting.
4. Apply filler (Plasmont) to any defects on the surface.
5. Pre-treat mouldy walls using Monto Limpia Moho.

WAY OF USE

Application notes

- Remove the product until perfectly homogeneous.
- Dilute the product according to the porosity and condition of the surface for the first coat.
- Finish with one or more slightly diluted coats until the surface is completely covered.
- Do not apply the product at temperatures below 5°C nor on surfaces exposed to strong sunshine.
- Do not wash for the first 24 days.
- Never apply it outdoors if there is an imminent risk of rain and avoid excessively wet days.
- Clean tools with water immediately after use.
- For spraying with Airless equipment, use 15 to 23 inch nozzles, pressure 150 bar.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	0-5%
Roller	0-5%
Air-less gun	10-20%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Inner painted old work in good state			
MAX			
STD	Ovaldine 65 Diluido		Ovaldine 65
Inner painted old work in good state			
MAX	Eliminar + Fijador	Ovaldine 65	Ovaldine 65
STD	Eliminar + Ovaldine 65 Diluido		Ovaldine 65
Project			
MAX	Fijador	Ovaldine 65	Ovaldine 65
STD	Ovaldine 65 Diluido		Ovaldine 65

Fecha de Alta

24-02-2026

Versión

2 - 24/03/2026 :

Drywall (gypsum plasterboard)

MAX	Ovaldine 65 Diluido	Ovaldine 65	Ovaldine 65
STD	Ovaldine 65 Diluido		Ovaldine 65

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5º and 35ºC

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

1 L, 4 L, 12 L