

Fecha de Alta

21-04-2021

Versión

8 - 21/08/2024



FAMILY ALTA DECORACION

LINE SISTEMA MICROCEMENTO

DESCRIPTION AND NATURE

Acrylic sealer for Microcement Ó deco. Regulates absorption, provides toughness. Very penetrating, great adhesion, transparent.

USAGES

Indoors/Outdoors

Ideal for varnishing Microcement Ó deco, on floors and walls.

PROPERTIES

Penetration power
 Good adhesion
 Excellent hardness
 Drying fast
 Good applicability
 Resists the alkaline pH of the support.
 Union bridge

TECHNICAL CHARACTERISTICS

Referencia Color	MICROCEMENT SEALER
Mixture relation	Uso
Finish	Transparent
Specific weight	0,98± 0,05 kg/l
Viscosity	11 +/- 1 SG
Solids in volume	17± 1
Solids in weight	17± 1
Aproximated performance by coat	16-18 m ² /L
Dry to touch	(20°C HR: 60%): 30min
Dry to repaint	(20°C HR: 60%): 4h
Colours	Transparent
Classification	AFNOR: NFT. 36005 - Famille I. Classe 7b2

SURFACE PREPARING

New surfaces

Over MICROCEMENT Ó deco cementitious:

- Depending on environmental conditions, wait at least 24 hours after applying Microcement Ó deco
- The support must be dry, clean, free of dust and oils.
- Eliminate large irregularities (burrs), by brushing or sanding with coarse grain.
- Condition with a medium grit sandpaper (150-220).
- Eliminate the dust generated by blowing air under pressure.
- Suction conveniently, helping us with a fine brush.

Restoring and maintenance

Fecha de Alta

21-04-2021

Versión

8 - 21/08/2024

WAY OF USE

Application notes

- Stir the product until it is perfectly homogenized.
- Respect the setting time of the MICROCEMENT Ó deco. We recommend waiting 48 hours.
- The humidity of the substrate must be less than 4%.
- Apply on clean and dry substrates.
- Do not apply the product at high temperatures, or on surfaces exposed to strong sunlight.
- Do not apply with relative humidity above 80%.
- Short hair roller.
- Consumption: 0.06 L/m² per hand. On Floors and Walls finishes 1 layer.
- We must ensure that it wets the entire surface well to extract all the air and prevent bubbles from being generated when it is varnished with the finish.
- On Rustic finish, 2 layers.
- Drying: minimum to overvarnish 4h, maximum 24h.
- It is essential to finish afterwards with Microcement Protector (2K) or Microcement Protector Deco (1K).

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	Usó
Roller	Usó
Air-less gun	Usó
Air-mix gun	Usó
Aerographic gun	Usó

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Complete system overview			
MAX	MICROCEMENT PRIMER ABS ó N-ABS	MICROCEMENT BASE + MICROCEMENT FLOORS/WALLS	SEALER + MICROCEMENT PROTECTOR (2K)
STD	MICROCEMENT BASE	MICROCEMENT FLOORS/WALLS	SEALER + MICROCEMENT PROTECTOR DECO (1K)
Microcement Ó deco			
MAX	MICROCEMENT PRIMER ABS ó N-ABS	MICROCEMENT BASE + MICROCEMENT FLOORS/WALLS	MICROCEMENT PROTECTOR (2K)
STD	MICROCEMENT BASE	MICROCEMENT FLOORS/WALLS	MICROCEMENT PROTECTOR DECO (1K)

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances.As it is impossible to stablish an adequate description for every nature and status of the supports to be

241927

MICROCEMENT SEALER



Fecha de Alta

21-04-2021

Versión

8 - 21/08/2024

painting, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

4 L, 800 L