



**FAMILY** MADERA / SISTEMAS TINTOMÉTRICOS

**LINE** MUEBLE (LACAS POLIURETANO)

## DESCRIPTION AND NATURE

Two-component white polyurethane finish. Matt. Good reactivity, hardness, touch and leveling. It stands out for its quality-price ratio and its quick drying.

## USAGES

Indoors

Wood treatment

Wood with sealer, and sanded

Product for exclusive use in industries regulated by Directive 2010/75 Chapter V.

## PROPERTIES

Adherence  
Optimal applicability  
High solid contents  
Strongness  
Elasticity  
Fast drying  
Odourless when dry  
Good coverage  
Good whiteness

## TECHNICAL CHARACTERISTICS

Referencia Color	MONTOPOL BLANCO MATE 59
Mixture relation	V: 2(Mpol)+1(Cat NA) P: 2.5+1
Finish	Matt
Specific weight	1,16± 0,05 kg/l
Viscosity	220 +/- 20 SG
Solids in volume	44± 1
Solids in weight	59± 1
Aproximated performance by coat	10-14 m <sup>2</sup> /L
Dry to touch	(20°C HR: 60%): 15-20 min
Dry to repaint	(20°C HR: 60%): 2-24 h
Colours	- Montomix Base (TR 19 - BL 59). Use NA Hardener. Wooden Letters 100 covering, RAL and NCS.

## SURFACE PREPAIRING

### New surfaces

New wood:

- The base must be free from foreign materials and/or waste matter.
- Apply to wood with a moisture content of less than 12%.
- Apply over a recommended base

### Restoring and maintenance

Varnished or painted wood:

- If in doubt, remove the previous varnish, lacquer or enamel.

- Apply over a recommended base

## WAY OF USE

### Application notes

- Stir the product until its perfect homogenization.
- Mix without modifying the proportions under any circumstances.
- Coat thicknesses greater than 130 g / m<sup>2</sup> wet should never be applied per coat.
- Always sand before applying the finishing varnish.
- Do not apply the product at high temperatures or on surfaces exposed to strong sunlight.
- Maintain good ventilation conditions during the drying time.
- Do not apply with relative humidity higher than 80%.
- Before mixing, check that the MONTOPOL NA HARDENER is completely transparent.
- Respect the minimum time between coats to avoid stirring.
- Respect the maximum time between coats to avoid adherence problems.

### Solvent for dilution and cleaning

Solvent PU 1410

Way of use	Aproximate dilution
Painting brush	0-5%
Air-less gun	5-10%
Air-mix gun	5-10%
Aerographic gun	0-20%

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Painted or varnished wood (closed pore) indoor</b>			
<b>MAX</b>	Decapar+ Montopol Fondo BL + Catalizador MS	Montopol Fondo BL + Catalizador MS	Montopol Blanco Mate 59 + Catalizador NA
<b>STD</b>	Decapar+ Montopol Fondo BL + Catalizador MS		Montopol Blanco Mate 59 + Catalizador NA
<b>Indoor wood (closed pore)</b>			
<b>MAX</b>	Montopol Fondo BL + Catalizador MS	Montopol Fondo BL + Catalizador MS	Montopol Blanco Mate 59 + Catalizador NA
<b>STD</b>	Montopol Fondo BL + Catalizador MS		Montopol Blanco Mate 59 + Catalizador NA
<b>Interior wood. Opaque lacquered finishes.</b>			
<b>MAX</b>	Montopol Fondo BL + Catalizador MS	Montopol Fondo BL + Catalizador MS	Montopol Blanco Mate 59 + Catalizador NA
<b>STD</b>	Montopol Fondo BL + Catalizador MS		Montopol Blanco Mate 59 + Catalizador NA

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Product of exclusive use for premises regulated under RD 117/2003 or 1999/13/CE regulations

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

5 Kg, 25 Kg



## FAMILY LINE

## DESCRIPTION AND NATURE

Two-component white polyurethane finish. Matt. Good reactivity, hardness, touch and leveling. It stands out for its quality-price ratio and its quick drying.

## USAGES


## PROPERTIES

- Adherence
- Optimal applicability
- High solid contents
- Strongness
- Elasticity
- Fast drying
- Odourless when dry
- Good coverage
- Good whiteness

## TECHNICAL CHARACTERISTICS

Referencia Color	
Mixture relation	V: 2(Mpol) + 1(Cat NA) P: 2.5 + 1
Finish	Matt
Specific weight	1,16 ± 0,05 kg/l
Viscosity	220 +/- 20 SG
Solids in volume	44 ± 1
Solids in weight	59 ± 1
Aproximated performance by coat	10-14 m <sup>2</sup> /L
Dry to touch	(20°C HR: 60%): 15-20 min
Dry to repaint	(20°C HR: 60%): 2-24 h
Colours	- Montomix Base (TR 19 - BL 59). Use NA Hardener. Wooden Letters 100 covering, RAL and NCS.

## SURFACE PREPARING



## New surfaces

New wood:

- The base must be free from foreign materials and/or waste matter.
- Apply to wood with a moisture content of less than 12%.
- Apply over a recommended base

## Restoring and maintenance

Varnished or painted wood:

- If in doubt, remove the previous varnish, lacquer or enamel.
- Apply over a recommended base

## WAY OF USE

### Application notes

- Stir the product until its perfect homogenization.
- Mix without modifying the proportions under any circumstances.
- Coat thicknesses greater than 130 g / m<sup>2</sup> wet should never be applied per coat.
- Always sand before applying the finishing varnish.
- Do not apply the product at high temperatures or on surfaces exposed to strong sunlight.
- Maintain good ventilation conditions during the drying time.
- Do not apply with relative humidity higher than 80%.
- Before mixing, check that the MONTOPOL NA HARDENER is completely transparent.
- Respect the minimum time between coats to avoid stirring.
- Respect the maximum time between coats to avoid adherence problems.

### Solvent for dilution and cleaning

Solvent PU 1410

Way of use	Aproximate dilution
Painting brush	0-5%
Air-less gun	5-10%
Air-mix gun	5-10%
Aerographic gun	0-20%

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Painted or varnished wood (closed pore) indoor</b>			
<b>MAX</b>	Decapar+ Montopol Fondo BL + Catalizador MS	Montopol Fondo BL + Catalizador MS	Montopol Blanco Mate 59 + Catalizador NA
<b>STD</b>	Decapar+ Montopol Fondo BL + Catalizador MS		Montopol Blanco Mate 59 + Catalizador NA
<b>Indoor wood (closed pore)</b>			
<b>MAX</b>	Montopol Fondo BL + Catalizador MS	Montopol Fondo BL + Catalizador MS	Montopol Blanco Mate 59 + Catalizador NA
<b>STD</b>	Montopol Fondo BL + Catalizador MS		Montopol Blanco Mate 59 + Catalizador NA
<b>Interior wood. Opaque lacquered finishes.</b>			
<b>MAX</b>	Montopol Fondo BL + Catalizador MS	Montopol Fondo BL + Catalizador MS	Montopol Blanco Mate 59 + Catalizador NA
<b>STD</b>	Montopol Fondo BL + Catalizador MS		Montopol Blanco Mate 59 + Catalizador NA

501615

Fecha de Alta

16-10-2007

Versión

1E - 19/06/2024

# MONTOPOL BLANCO MATE 59 NA



## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Product of exclusive use for premises regulated under RD 117/2003 or 1999/13/CE regulations

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

## PACKINGS

5 Kg, 25 Kg