

Fecha de Alta

27-01-2009

Versión

17 - 31/12/2025


**FAMILY** ESMALTES / SISTEMAS TINTOMÉTRICOS

**LINE** SINTETICOS METAL-MADERA

**DESCRIPTION AND NATURE**

Pigmented gloss glycerophthalic synthetic enamel, recommended in alkyd systems on steel, wood and plasterwork.

**USAGES**

Outdoors/Indoors

Metal after priming

Wood

Construction

In order to apply on galvanized steel to consult with the technical department

**PROPERTIES**

Makes a film  
 Penetrating depth  
 Strong resistance to the atmospherical factors  
 With micronic pigments wich are UV protectives  
 No cracking at all  
 Odourless when dry  
 Good applicability  
 Does not form blisters

**TECHNICAL CHARACTERISTICS**

Referencia Color	MARISMA BRILLO BLANCO
Finish	Gloss
Specific weight	1,12± 0,05 kg/l
Viscosity	75 +/- 5 KU
Solids in volume	29± 1
Solids in weight	50± 1
VOC	Cat. d/BD 400/300 (2007/2010): 269,07 g/l
Aproximated performance by coat	12-14 m <sup>2</sup> /L

Dry to touch	(20°C HR: 60%): 2-4h
Dry to repaint	(20°C HR: 60%): 24h
Colours	White 100 Colours on the Marisma chart Bases BL, IN and TR Colors of the Tintometric System

**SURFACE PREPAIRING**
**New surfaces**

New wood surfaces:

1. The base must be free from foreign materials and/or waste products.
2. Apply on wood with a moisture content of less than 20%.
3. Apply on healthy wood that is dry and free of grease and dust.
4. Sand down and remove any remains of glue in joints and defects from mechanical processes.
5. If the wood shows signs of ageing it must first be sanded down, primed and any dust removed by brushing or any other mechanical device.
6. In this instance the most suitable primer is Selladora Sellalux.

Fecha de Alta

27-01-2009

Versión

17 - 31/12/2025

**Iron and derivatives:**

1. To protect the surface, prior to decoration work, treat with suitable primers (family 6) following the specifications given on the product information sheet.
2. The surface to be painted must be free of other products and/or residues, grease and dust free, and dry. Any signs of rust should be removed by brushing or any other mechanical means. Oxifin may also be used (see product technical information sheet).

**Works (plaster/ gypsum, cement and derivatives):**

1. Treat these surfaces in the usual way, removing saltpetre, excess moisture and efflorescence.
2. Remove foreign products and/or waste matter.
3. Once dry, prime using Imprimpación Sellalux.

**Restoring and maintenance****Varnished or painted wood:**

1. If varnished using Montoxyl colour: remove foreign products, remove any loose or peeling varnish, lightly sand, remove dust from sanding and proceed as on new wood.
2. If varnished, remove this by stripping with Quitamont Universal or by mechanical means and proceed as on new wood.
3. If coated with a synthetic enamel (Montosintético, Marisma, Luxatin or similar), open the pore by sanding, remove the resulting dust and proceed as with new wood.

**Iron and enamelled derivatives:**

1. On paintwork that is in good condition sand down to open pore, checking that the adhesion of the paint is perfect.
2. On paint in poor condition, remove using mechanical or chemical means and proceed as on a new surface.

**WAY OF USE****Application notes**

- Stir the product until perfectly blended.
- Apply, following the rules set out in the attached application table.
- To print previously, on new wood, with Klearxyl Di if a preventive protection against fungi and insects is desired.
- Do not apply the product in extreme temperatures, or on surfaces exposed to strong sunlight.
- Keep the space well ventilated while the product is drying.
- Do not apply with relative humidity above 80%.

**Solvent for dilution and cleaning**

Solvent 1401

**Way of use**

Brush, Roller

**Aproximate dilution**

Al uso

**SYSTEM****Procedures depending of surface type**

	Primer	Intermedium	Finish
<b>New work</b>			
<b>MAX</b>			
<b>STD</b>		Selladora Sellalux o Selladora Acqua Blanca	Marisma brillante
<b>Metal</b>			
<b>MAX</b>			
<b>STD</b>	Impriepox M-10, Impripol, Minio Blanco, Imprim. Sintética, Imprim. Industrial	Impriepox M-10, Impripol, Minio Blanco, Imprim. Sintética, Imprim. Industria	Marisma brillante
<b>Wood</b>			
<b>MAX</b>			
<b>STD</b>	Selladora Sellalux o Selladora Acqua Blanca	Selladora Sellalux o Selladora Acqua Blanca	Marisma brillante

Fecha de Alta

27-01-2009

Versión

17 - 31/12/2025

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

0.375 L, 15 L

Canned bases 0.75 L, 4 L