

Fecha de Alta

27-02-2014

Versión

8 - 20/01/2026



FAMILY PAVIMENTOS

LINE SEÑALIZACIÓN VIAL (AGUA)

## DESCRIPTION AND NATURE

Semi-gloss protective varnish for cement floors, terraces, etc.  
 Varnish to improve the resistance and shine of paints such as Pavimont.  
 Varnish for wood floors.  
 Varnish for wood surfaces and furniture in general.

## USAGES

Outdoor/Indoor  
 Cement  
 Moulded concrete  
 Concrete  
 Cement mortars  
 Wood

## PROPERTIES

Strongness  
 Surface protection  
 Odourless when dry  
 Resistance to friction and hits  
 Anti-dust  
 Resistant to washing  
 Easily applicable  
 Water-based  
 Drying fast  
 U.V. resistant

## TECHNICAL CHARACTERISTICS

Referencia Color	BARNIZ PAVIMONT ACQUA
Finish	Semi-gloss
Specific weight	1 ± 0,05 kg/l
Viscosity	55 +/- 5 SG
Solids in volume	24 ± 1
Solids in weight	26 ± 1
VOC	Cat. i/BA 140/140 (2007/2010): 73,65 g/l
Aproximated performance by coat	Depending of product usage
Dry to touch	30-60min
Dry to repaint	12-24h

## SURFACE PREPAIRING

## New surfaces

Masonry surfaces (cement and derivatives):

1. Treat these surfaces in the usual way, removing saltpetre, excess moisture and efflorescence.
2. Treat the surface to achieve the desired porosity.
3. Remove foreign products and/or residues.

Wood:

1. The surface must be free from foreign products and/or residues.

Fecha de Alta

27-02-2014

Versión

8 - 20/01/2026

2. Apply to sound dry wood, well cleaned of dust and grease.
3. Sand and eliminate residues and flaws from the surface.

### Restoring and maintenance

Varnished or painted wood:

Strip, sand and treat as new wood.

## WAY OF USE

### Application notes

- With very absorbent surfaces a primer/fixative is recommended before applying Barniz Pavimont Acqua. A spot test before application is always advisable.
- Stir the product until perfectly blended.
- Do not apply the product at high temperatures or on surfaces exposed to strong insolation.
- Humidity of flooring: maximum of 4% measured at a depth of 2 cm.

### Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Brush, roller or spray gun	AL USO

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Cement</b>			
<b>MAX</b>	BARNIZ PAVIMONT ACQUA		BARNIZ PAVIMONT ACQUA
<b>STD</b>	BARNIZ PAVIMONT ACQUA		BARNIZ PAVIMONT ACQUA
<b>Wood</b>			
<b>MAX</b>	BARNIZ PAVIMONT ACQUA		BARNIZ PAVIMONT ACQUA
<b>STD</b>	BARNIZ PAVIMONT ACQUA		BARNIZ PAVIMONT ACQUA

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

4 L, 15 L