

Fecha de Alta

23-04-2008

Versión

8 - 16/01/2026



**FAMILY**  
**LINE**

PRODUCTOS PARA USO ESPECIFICO

FRONTON

### DESCRIPTION AND NATURE

Long-lasting, highly resistant water-based acrylic paint for the protection, maintenance and marking of pediments.

### USAGES

Outdoors/Indoors

Cement

Tennis court

### PROPERTIES

Elasticity  
Surface leveling  
Resistance to hits  
Alacalynity resistance  
Good coverage  
Good adhesion  
Non Yellowing  
Strong resistance to the atmospherical factors  
Does not spread flame  
AFNOR T. 30.003 - FAMILIA I CLASE 7b2 - CLASSIFIED  
Good performance

### TECHNICAL CHARACTERISTICS

Referencia Color	MONTOSPORT FRONTON VERDE
Finish	Smooth
Specific weight	1,36± 0,05 kg/l
Viscosity	90 +/- 20 PO
Solids in volume	47± 1
Solids in weight	62± 1
Aproximated performance by coat	8-10 m <sup>2</sup> /L

Dry to touch	(20°C HR: 60%): 15-45min
Dry to repaint	(20°C HR: 60%): 3-6h
Colours	Green 128.

### SURFACE PREPAIRING

#### New surfaces

Cement mortars:

1. Wait until fully hardened (min. 30 days).
2. Clean off possible efflorescence with an abrasive jet.
3. Neutralise alkaline surfaces.
4. For polished surfaces: sand down to open the grain.
5. Clean any unusual products from the base.
6. Fix crumbling bases using fixative emulsion or Fijamont.
7. Fill in any defects/flaws in the base (see family 6).

Plaster:

1. Wait until the plaster is dry (maximum 20% humidity).

Fecha de Alta

23-04-2008

Versión

8 - 16/01/2026

2. Clean any unusual products from the base.
3. Clean off possible efflorescence with an abrasive jet.
4. Control the absorbency of the base using a sealer, fixative emulsion or a diluted coat of the same product.
5. For polished surfaces: sand down to open the grain.
6. Fix crumbling bases using fixative emulsion or Fijamont.
7. Fill in any defects in the base (see family 6). Cement mortar, plaster and by-products.

#### Restoring and maintenance

1. Completely remove any old loose paint.
2. Dull down glossy surfaces to ensure good adhesion.
3. On painted bases, check the solidity and fastening of the paint and the type of paint to avoid potential incompatibilities and remove dust and dirt before repainting.
4. Fill in any defects in the base using plaster (Plasmont).
5. Walls with mould, treat first with Monto Limpia Moho.

## WAY OF USE

#### Application notes

- Stir the product until perfectly blended.
- Dilute the product according to the porosity and state of the base on the first coat.
- Finish with one or two slightly diluted coats, until the base is fully covered.
- Do not apply the product at temperatures below 5°C, or on surfaces exposed to strong insolation.
- Do not wash until after 25-30 days.

#### Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	10-20%
Roller	10-20%
Air-less gun	5-20%
Air-mix gun	5-20%
Aerographic gun	15-30%
Low pressure turbo	15-30%

## SYSTEM

#### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Support with mould</b>			
<b>MAX</b>	Monto Limpia Moho	Montosport Frontón+Monto Aditivo con conservante antimoho	Montosport Frontón+Monto Aditivo con conservante antimoho
<b>STD</b>	Monto Limpia Moho	Montosport Frontón+Monto Aditivo con conservante antimoho	Montosport Frontón+Monto Aditivo con conservante antimoho
<b>Old paintings in bad state</b>			
<b>MAX</b>	Fijador, Emulsión Fijadora	Montosport Frontón	Montosport Frontón
<b>STD</b>	Montosport Frontón diluido		Montosport Frontón
<b>Asphalt fabric</b>			
<b>MAX</b>			
<b>STD</b>	Montosport Frontón diluido		Montosport Frontón
<b>Wood</b>			
<b>MAX</b>	Selladora Sellalux	Montosport Frontón	Montosport Frontón
<b>STD</b>	Pasta mate industrial diluida		Montosport Frontón
<b>Project</b>			

Fecha de Alta

23-04-2008

Versión

8 - 16/01/2026

---

<b>MAX</b>	Fijador, Emulsión Fijadora	Montosport Frontón	Montosport Frontón
<b>STD</b>	Montosport Frontón diluido		Montosport Frontón

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

12 L