

Fecha de Alta

18-11-2022

Versión

1E - 04/12/2025



FAMILY

PAREDES Y TECHOS / SISTEMAS TINTOMÉTRICOS

LINE

MATE

### DESCRIPTION AND NATURE

Sanitizing matte plastic paint. ZERO bacteria and ZERO mold. With antibacterial activity certificate: it incorporates silver ions that give the dry paint film already applied, resistance to the growth of bacteria (reduction of 99.9% in 24 hours) and molds. ZERO emissions and ZERO odor: with A + low emission certificate, it also has a very low concentration of volatile organic compounds VOC: 0.2 g / l, 150 times less than required for its category. It does not emit an odor when applied, it allows you to enable spaces immediately without discomfort. This product contributes to LEED®, BREEAM® and VERDE certifications.

### USAGES

Indoors/Outdoors

Sports centres, indoor swimming pools, changing rooms, etc.

Food processing plants, supermarkets, etc

Clinics, hospitals, homes for the elderly, schools, nurseries, etc.

Walls and ceilings

Cement mortars

Concrete

Brick

Plaster

Dripping effect

Drywall (gypsum plasterboard): fibreboard

Because of its low emission and low odour properties, it is particularly recommended for indoor use

### PROPERTIES



Low odour

Security Certification for Toys according to Standard EN 71-3:2013 + A1:2014

Reaction to fire classification: B-s1,d0 according to standard UNE-EN 13501-1

Gloss level: matt (according to UNE-EN 13300, at 85° reflectance &lt; 10)

Opacity: Class 1 for a performance of 5.5 m<sup>2</sup>/litre (according to Standard UNE-EN 13300). This information may vary depending on the colour chosen.

Mildew-proof film. Paint with anti-mildew preservative to prevent the spread of fungus on the applied paint film, once dried.

Emission free paint. Tested and classified as class A+ after 28 days of trials in WESSLING laboratories (certified to conduct trials in emission chambers).

According to Eurofins Biolab S.r.l. based on the results obtained, interpreted according to ASTM E 2180-2007, it has antibacterial activity that causes a 99.84% reduction against *Staphylococcus aureus* and a 99.89% against *Pseudomonas aeruginosa*, after 24h of contact

Washability: Class 2 (according to Standard UNE-EN 13300)

According to AINIA, and based on the results obtained, interpreted according to the ISO21702:2019 standard, it has antiviral activity: 99.99% reduction of feline Calicivirus; 99.94% reduction of human Coronavirus; 99.17% reduction of Influenzavirus A, after 24 hours of contact

Gardner Washability Standard DIN 53778: 8.000 d.p

Fecha de Alta

18-11-2022

Versión

1E - 04/12/2025



## TECHNICAL CHARACTERISTICS

Referencia Color	UNO ZERO BLANCO
Finish	.
Specific weight	1,53± 0,05 kg/l
Viscosity	90 +/- 15 PO
Solids in volume	43± 1
Solids in weight	64± 1
VOC	Cat. a/BA 75/30 (2007/2010):0,15 g/l
Aproximated performance by coat	12-14 m <sup>2</sup> /L
Dry to touch	(20°C HR:60%): 1h
Dry to repaint	(20°C HR:60%): 3-4h
Colours	White BL base Tintometric System Colours.

## SURFACE PREPAIRING

### New surfaces

Cement and concrete mortars:

1. Wait until fully set (min. 30 days).
2. Clean any efflorescence with a jet washer.
3. Neutralize alkaline surfaces.
4. Sand polished surfaces to create a rougher surface.
5. Clean the surface to remove foreign products.
6. Set crumbly substrates with Emulsión Fijadora or Fijamont.
7. Fill in defects in the substrate (see family 6).

Plaster, plaster-covered brick:

1. Wait until it is completely dry (max. 20% humidity).
2. Clean the surface to remove foreign products.
3. Clean any efflorescence with a jet washer.
4. Regulate surface absorption with sealer, fixer, or a diluted coat of the same product.
5. Sand polished surfaces to create a rougher surface.
6. Set crumbly substrates with Emulsión Fijadora or Fijamont.
7. Fill in defects in the substrate (see family 6).

Plasterboard partition walls:

1. Carry out a general sanding of the joints and putty fixing areas.
2. Then, clean them to ensure the substrate is free of dust, grease and other contaminants.
3. For application on coloured boards that tend to generate stains, apply Montoplac Sellador Antimanchas.

### Restoring and maintenance

1. Completely remove old paint that is in poor condition or that is poorly-adhered.
2. Glossy surfaces should be thinned out to ensure good adhesion.
3. On painted surfaces, check that the paint is solid and well-adhered. Its condition must be assessed, in order to avoid possible incompatibilities. Dust and dirt must also be eliminated before repainting.
4. Apply filler (Plasmont) to any defects on the surface.

Fecha de Alta

18-11-2022

Versión

1E - 04/12/2025

5. Pre-treat mouldy walls using Monto Limpia Moho.

## WAY OF USE

### Application notes

- Remove the product until perfectly homogeneous.
- Dilute the product according to the porosity and condition of the surface for the first coat.
- Finish with one or more slightly diluted coats until the surface is completely covered.
- Do not apply the product at temperatures below 5°C nor on surfaces exposed to strong sunshine.
- Do not wash for the first 24 days.
- Clean tools with water immediately after use.
- Never apply it outdoors if there is an imminent risk of rain, and avoid excessively wet days.
- For spraying with Airless equipment, use 15 to 23 inch nozzles, pressure 150 bar.

### Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	5-20%
Roller	5-20%
Air-less gun	5-30%

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>Inner painted old work in good state</b>			
<b>MAX</b>			
<b>STD</b>	Uno Zero Diluido		Uno Zero
<b>Inner painted old work in good state</b>			
<b>MAX</b>	Eliminar + Fijador	Uno Zero	Uno Zero
<b>STD</b>	Eliminar + Uno Zero Diluido		Uno Zero
<b>Project</b>			
<b>MAX</b>	Fijador	Uno Zero	Uno Zero
<b>STD</b>	Uno Zero Diluido		Uno Zero
<b>Drywall (gypsum plasterboard)</b>			
<b>MAX</b>	Uno Zero Diluido	Uno Zero	Uno Zero
<b>STD</b>	Uno Zero Diluido		Uno Zero

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances.As it is impossible to stablish an adecuate description for every nature and status of the supports to be

502256

# UNO ZERO



Fecha de Alta

18-11-2022

Versión

1E - 04/12/2025

---

painting, we are unable to warrant the absolute reproductibility in each specific use

## PACKINGS

1 L, 4 L, 12 L, 15 L