

Fecha de Alta

08-08-2006

Versión

5 - 09/01/2026


FAMILY PREPARACIONES, FONDOS E IMPR.

LINE MASILLAS EN POLVO

DESCRIPTION AND NATURE

Universal powder filler, suitable for filling large defects and smoothing small imperfections. Easy to apply. Excellent whiteness and adhesion. Good sandability. When painting, the filled areas do not show through.

USAGES

Indoors

Cement

Walls made of brick or other materials that tend to leave marks or stains when painted

Wood

Concrete

Plaster

PROPERTIES

High and medium thickness finishings

Fast hardening

Smooth rugged touch

Easy mixing

Do not come in clots

TECHNICAL CHARACTERISTICS

Referencia Color	PLASMONT MULTIUSO
Mixture relation	450-550 ml de agua por kg masilla
Finish	Matt
Specific weight	2,42± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 4-5h
Dry to repaint	(20°C HR: 60%): 24-48h
Colours	White

SURFACE PREPAIRING
New surfaces

Cement/plaster mortar:

- Check suitability of PLASMONT MULTIUSO on surface.
- Allow to harden completely (minimum 30 days).
- Remove possible efflorescence and neutralise alkaline surfaces.
- Sand to open the pores of excessively polished surfaces.
- Remove external products and/or residues.
- Back gouge any cracks or fissures down to repaired base, remove subsequent dust with brush and apply PLASMONT MULTIUSO filler as instructed in the Application Systems and Applications.
- Do not exceed the maximum recommended thickness of coats.
- On surfaces in an excessively poor condition suitable fixative should be used before applying filler (see product family 6).

Wood:

- Check suitability of PLASMONT MULTIUSO on surface.
- Sand to open pores of excessively polished surfaces.

Fecha de Alta

08-08-2006

Versión

5 - 09/01/2026

- Remove external products and/or residues.
- Back gouge any cracks or fissures down to repaired base, remove subsequent dust with brush and apply PLASMONT MULTIUSO filler as instructed in the Application Systems and Applications.
- Do not exceed the maximum recommended thickness of coats.
- Apply on healthy, grease-free, resin free, dust free and dry wood with less than 20% internal dampness. If the wood shows signs of ageing it should be sanded and the cracks back gouged to healthy wood.

Restoring and maintenance

- Remove off any remains or chipping of product or any other foreign product. Open pore by sandpàpering or any other mechanical systems. Test adherence level and treat as per new surfaces.

WAY OF USE**Application notes**

- Dilute with clean, unpolluted water.
- Use the tools indicated in the application system instructions. Ensure the tools are clean, in good working order and of course, rust free.
- Maximum thickness per layer: 5mm
- Repaint following the indicated period of time. Given that this depends on the levels of humidity, temperature and thickness of the coating, the lack of clogging of the sandpaper with indicate that the product is ready for repainting.

Solvent for dilution and cleaning

Water

Way of use

Stainless trowel

Pallette / spatula

Pallette

Aproximate dilution

450-550 ml agua/kg masilla

450-550 ml de agua/kg masilla

450-550 ml de agua/kg masilla

SYSTEM**Procedures depending of surface type**

	Primer	Intermedium	Finish
Wood			
MAX	Selladora sellalux	Selladora sellalux	Fijador+Montoplástica o Familia 4
STD	Plasmont Multiusos Standar		Montoplástica o Familia 4
Project			
MAX	Fijador (Emulsión Fijadora Fijamont)	Plasmont Multiusos Standar	Fijador+Montoplástica, Familia 4
STD	Plasmont Multiusos Standar		Montoplástica, Familia 4

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Fecha de Alta

08-08-2006

Versión

5 - 09/01/2026

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

1 Kg, 5 Kg, 15 Kg



FAMILY LINE

DESCRIPTION AND NATURE

Universal powder filler, suitable for filling large defects and smoothing small imperfections. Easy to apply. Excellent whiteness and adhesion. Good sandability. When painting, the filled areas do not show through.

USAGES

PROPERTIES

High and medium thickness finishings
Fast hardening
Smooth rugged touch
Easy mixing
Do not come in clots

TECHNICAL CHARACTERISTICS

Referencia Color	
Mixture relation	450-550 ml de agua por kg masilla
Finish	Matt
Specific weight	2,42± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 4-5h
Dry to repaint	(20°C HR: 60%): 24-48h
Colours	White

SURFACE PREPAIRING

New surfaces

Cement/plaster mortar:

- Check suitability of PLASMONT MULTIUSO on surface.
- Allow to harden completely (minimum 30 days).

Fecha de Alta

08-08-2006

Versión

5 - 09/01/2026

- Remove possible efflorescence and neutralise alkaline surfaces.
- Sand to open the pores of excessively polished surfaces.
- Remove external products and/or residues.
- Back gouge any cracks or fissures down to repaired base, remove subsequent dust with brush and apply PLASMONT MULTIUSO filler as instructed in the Application Systems and Applications.
- Do not exceed the maximum recommended thickness of coats.
- On surfaces in an excessively poor condition suitable fixative should be used before applying filler (see product family 6).

Wood:

- Check suitability of PLASMONT MULTIUSO on surface.
- Sand to open pores of excessively polished surfaces.
- Remove external products and/or residues.
- Back gouge any cracks or fissures down to repaired base, remove subsequent dust with brush and apply PLASMONT MULTIUSO filler as instructed in the Application Systems and Applications.
- Do not exceed the maximum recommended thickness of coats.
- Apply on healthy, grease-free, resin free, dust free and dry wood with less than 20% internal dampness. If the wood shows signs of ageing it should be sanded and the cracks back gouged to healthy wood.

Restoring and maintenance

- Remove off any remains or chipping of product or any other foreign product. Open pore by sandpàpering or any other mechanical systems. Test adherence level and treat as per new surfaces.

WAY OF USE**Application notes**

- Dilute with clean, unpolluted water.
- Use the tools indicated in the application system instructions. Ensure the tools are clean, in good working order and of course, rust free.
- Maximum thickness per layer: 5mm
- Repaint following the indicated period of time. Given that this depends on the levels of humidity, temperature and thickness of the coating, the lack of clogging of the sandpaper with indicate that the product is ready for repainting.

Solvent for dilution and cleaning

Water

Way of use

Stainless trowel
Pallette / spatula
Pallette

Aproximate dilution

450-550 ml agua/kg masilla
450-550 ml de agua/kg masilla
450-550 ml de agua/kg masilla

SYSTEM**Procedures depending of surface type**

	Primer	Intermedium	Finish
Wood			
MAX	Selladora sellalux	Selladora sellalux	Fijador+Montoplástica o Familia 4
STD	Plasmont Multiusos Standar		Montoplástica o Familia 4
Project			
MAX	Fijador (Emulsión Fijadora Fijamont)	Plasmont Multiusos Standar	Fijador+Montoplástica, Familia 4
STD	Plasmont Multiusos Standar		Montoplástica, Familia 4

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

502312


PLASMONT MULTIUSO

Fecha de Alta

08-08-2006

Versión

5 - 09/01/2026



Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

PACKINGS

1 Kg, 5 Kg, 15 Kg