

PLASMONT EXTERIORES R20 BLANCO



FAMILY PREPARACIONES, FONDOS E IMPR.

LINE MASILLAS EN POLVO

DESCRIPTION AND NATURE

Powdered cement filler for exteriors, for plaster finishing and repairing surfaces. Can be sanded and painted once dry.

USAGES

Concrete
Cement mortars
Mineral media
Exterior, fissures repairation, hole filler
Masonry repair

PROPERTIES

Adherence
Strongness
Whiteness
Adequate for High thickness coats
Able to be sanded
Coverage of 1mm thickness: 1.75 kg / m²
Fast hardening
Smooth rugged touch
Fast repainting
Easy application
Easy to repaint

TECHNICAL CHARACTERISTICS

Referencia Color	PLASMONT EXTERIORES R20 BLANCO
Mixture relation	350 - 425 gr de agua / 1000gr Plasmont Exteriores
Mixture lasting	2 h
Finish	Matt
Specific weight	2,55± 0,05 kg/l
Solids in volume	100± 1
Solids in weight	100± 1
Minimum recommended thickness	2 cm (máximo)
Aproximated performance by coat	Depending of product usage
Dry to touch	(20°C HR: 60%): 2-4h
Dry to repaint	(20°C HR: 60%): 24-48h
Colours	White

SURFACE PREPARING

New surfaces

Cement mortar/plaster:

- Check the suitability of PLASMONT EXTERIORES R20 BLANCO for the base.
- Wait until the surface is totally hardened (28 days for cement and concrete).
- Clean possible efflorescence from the base and neutralise alkaline surfaces.
- Sand down excessively polished surfaces to open the pore.
- Clean any foreign products and/or residues from the base.

Fecha de Alta

23-11-2015

Versión

5 - 09/01/2026

- Open up any cracks and fissures until the base is cleaned up, remove the dust produced with a brush and apply PLASMONT EXTERIORES R20 BLANCO as indicated in the Application Systems and Application sections.
- Never exceed the maximum recommended layer thickness.
- Fix very crumbly surfaces with a suitable fixative before filling (see Family 6).

Restoring and maintenance

1.- Remove any foreign products and paint that is loose or in poor condition, opening up the grain if necessary through sanding or other mechanical means. Check the adhesion and treat as a new BASE.

WAY OF USE

Application notes

- Use clean, uncontaminated water to dilute.
- Use the tools indicated under application methods, clean and free of rust.
- Paint and sand after enough time has passed for the product to dry. Given that this depends on humidity, temperature and the thickness of the coat, when sandpaper does not clog, this indicates that the product is ready for painting.
- Fast painting option: 24-48 hours depending on the thickness of the coat and weather conditions.

Solvent for dilution and cleaning

Water

Way of use

Stainless trowel

Pallette / spatula

Pallette

Aproximate dilution

350-425 ml agua por kg

350-400 ml agua por kg

350-425 ml

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New work			
MAX			
STD	Plasmont Exteriores R20 Blanco	Fijador (Emulsión Fijadora o Fijamont)	Pinturas plásticas, Revestimientos, Esmaltes
Works with plaster finishing			
MAX			
STD	Plasmont Exteriores R-20 Blanco	Fijador (Emulsión Fijadora o Fijamont)	Pinturas plásticas, Revestimientos, Esmaltes

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances.As it is impossible to stablish an adequate description for every nature and status of the supports to be

PLASMONT EXTERIORES R20 BLANCO

Painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

1 Kg, 5 Kg, 15 Kg



FAMILY LINE

DESCRIPTION AND NATURE

Powdered cement filler for exteriors, for plaster finishing and repairing surfaces. Can be sanded and painted once dry.

USAGES

PROPERTIES

Adherence
Strongness
Whiteness
Adequate for High thickness coats
Able to be sanded
Coverage of 1mm thickness: 1.75 kg / m²
Fast hardening
Smooth rugged touch
Fast repainting
Easy application
Easy to repaint

TECHNICAL CHARACTERISTICS

Referencia Color

Mixture relation 350 - 425 gr de agua / 1000gr Plasmont Exteriores

Mixture lasting 2 h

Finish Matt

Specific weight 2,55± 0,05 kg/l

Solids in volume 100± 1

Solids in weight 100± 1

Minimum recommended thickness 2 cm (máximo)

Aproximated performance by coat Depending of product usage

Dry to touch (20°C HR: 60%): 2-4h

Dry to repaint (20°C HR: 60%): 24-48h

Colours White

SURFACE PREPARING

New surfaces

Cement mortar/plaster:

- Check the suitability of PLASMONT EXTERIORES R20 BLANCO for the base.
- Wait until the surface is totally hardened (28 days for cement and concrete).
- Clean possible efflorescence from the base and neutralise alkaline surfaces.
- Sand down excessively polished surfaces to open the pore.

Fecha de Alta

23-11-2015

Versión

5 - 09/01/2026

- Clean any foreign products and/or residues from the base.
- Open up any cracks and fissures until the base is cleaned up, remove the dust produced with a brush and apply PLASMONT EXTERIORES R20 BLANCO as indicated in the Application Systems and Application sections.
- Never exceed the maximum recommended layer thickness.
- Fix very crumbly surfaces with a suitable fixative before filling (see Family 6).

Restoring and maintenance

1.- Remove any foreign products and paint that is loose or in poor condition, opening up the grain if necessary through sanding or other mechanical means. Check the adhesion and treat as a new BASE.

WAY OF USE

Application notes

- Use clean, uncontaminated water to dilute.
- Use the tools indicated under application methods, clean and free of rust.
- Paint and sand after enough time has passed for the product to dry. Given that this depends on humidity, temperature and the thickness of the coat, when sandpaper does not clog, this indicates that the product is ready for painting.
- Fast painting option: 24-48 hours depending on the thickness of the coat and weather conditions.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Stainless trowel	350-425 ml agua por kg
Pallette / spatula	350-400 ml agua por kg
Pallette	350-425 ml

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New work			
MAX			
STD	Plasmont Exteriores R20 Blanco	Fijador (Emulsión Fijadora o Fijamont)	Pinturas plásticas, Revestimientos, Esmaltes
Works with plaster finishing			
MAX			
STD	Plasmont Exteriores R-20 Blanco	Fijador (Emulsión Fijadora o Fijamont)	Pinturas plásticas, Revestimientos, Esmaltes

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

502352

Fecha de Alta

23-11-2015

Versión

5 - 09/01/2026

PLASMONT EXTERIORES R20 BLANCO



NOTE

PACKINGS

1 Kg, 5 Kg, 15 Kg