

Fecha de Alta

19-09-2008

Versión

14 - 10/11/2025

Specific weight	1,43± 0,05 kg/l
Viscosity	60 +/- 5 PO
Solids in volume	39± 1
Solids in weight	59± 1
VOC	Cat. c/BA 75/40 (2007/2010): 1,84 g/l
Aproximated performance by coat	6-10 m ² /L

Dry to touch	(20°C HR: 60, 60 microns): 1-2 h
Dry to repaint	(20°C HR: 60, 60 microns): 4-6 h
Colours	White and colors

SURFACE PREPAIRING

New surfaces

Cement Mortar:

1. Wait until total drying (minimum 30 days).
2. Clean any efflorescence with abrasive blasting.
3. Neutralize the alkaline surfaces.
4. On slick surfaces, sanding to open pore.
5. Clear support for foreign products.
6. Fix crumbly surfaces with a suitable fixative (see Family 6).
7. Cover surface imperfections with plaster or putty (See Family 6).

Restoring and maintenance

1. Eliminate completely the old paint in poor condition or poorly attached.
2. Glossy surfaces must be tempered to ensure good adhesion.
3. In painted supports it should be checked the strenght and anchoring of the painting, diagnose their nature to avoid potential incompatibilities and remove dust and dirtiness before being repainted.
4. Putty with putty the defects of the support (see family 6 the putty products and ready putties to make an educated choice).
5. Treat with Monto Limpia Moho the supports with mold.

WAY OF USE

Application notes

- Stir until perfect homogenization.
- Dilute the product in terms of porosity and state of the support.
- In the first coat high dilutions are recommended that could reach 40%. In this way the product will penetrate the maximum in the support.
- It is recommended total layer thickness of around 250 microns wet.
- Apply to clean and dry substrates.
- Apply following the instructions marked on the attached application chart.
- Do not apply the product at high temperatures, or on surfaces exposed to intense sunlight.
- Do not apply at temperatures below 5°C.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	10-20%
Roller	10-20%
Air-less gun	10-25%
Air-mix gun	10-25%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Masonry mortar			

Fecha de Alta

19-09-2008

Versión

14 - 10/11/2025

MAX	Fijamont, Emulsión Fijadora	Hormimont Acrílico	Hormimont Acrílico
STD	Hormimont Acrílico diluido		Hormimont Acrílico

Reinforced Concrete

MAX	Fijamont, Emulsión Fijadora	Hormimont Acrílico	Hormimont Acrílico
STD	Hormimont Acrílico diluido		Hormimont Acrílico

Support with mould

MAX	Monto Limpia Moho + Fijamont, Emulsión Fijadora	Hormimont Acrílico	Hormimont Acrílico + Monto Aditivo con conservante antimoho
STD	Hormimont Acrílico diluido		Hormimont Acrílico + Monto Aditivo con conservante antimoho

New work

MAX	Fijamont, Emulsión Fijadora	Hormimont Acrílico	Hormimont Acrílico
STD	Hormimont Acrílico diluido		Hormimont Acrílico

Old paintings in bad state

MAX	Eliminar + Fijamont, Emulsión Fijadora	Hormimont Acrílico	Hormimont Acrílico
STD	Eliminar + Hormimont Acrílico diluido		Hormimont Acrílico

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

15 L