

Fecha de Alta

12-01-2021

Versión

9 - 21/04/2026



FAMILY REVESTIMIENTOS DE FACHADAS / SISTEMAS TINTOMÉTRICOS
LINE SILICATO

DESCRIPTION AND NATURE

Smooth silicate coating, for protecting and decorating façades and exterior walls. Deep mineral matt appearance that conceals imperfections. Stops the spread of mould. It provides high durability and resistance on mineral substrates where maximum adherence and breathability is obtained, avoiding the accumulation of dampness and the formation of blisters and flaking. Ideal for professional application: high coverage, high performance, low gloss and fast execution. This product contributes to LEED®, BREEAM® and VERDE certifications.

USAGES

Outdoors/Indoors
 Facades
 Stone
 Restoring historic centres
 Mineral media
 Cement mortars
 Concrete
 Lime Mortars

PROPERTIES

Washability: Class 2 (according to Standard UNE-EN 13300)
 Gloss level: extra matt (according to UNE-EN 13300, at 85° reflectance < 5)
 Water vapour permeability: V1 (maximum breathability) (according to standard UNE-EN 1062-1)
 Dry film thickness: E2 (between 50 and 100 microns, according to UNE-EN 1062-1 standard) for average performance with two coats (see Technical Characteristics)
 Opacity: Class 1 for a performance of 5 m²/litre (according to Standard UNE-EN 13300). This information may vary depending on the colour chosen.
 Gloss: G3 (matt, according to the UNE-EN 1062-1 standard)
 Amount of organic matter < 5% (Standard UNE EN 48312)
 Liquid water permeability: W1 (impermeable) (according to UNE-EN 1062-1)
 The product can be guaranteed for up to 12 years for white and 10 for COF and FE, see conditions
 Meets Indoor Air Comfort Gold emissions test (Eurofins) (only in white)



TECHNICAL CHARACTERISTICS

Referencia Color	OVALDINE SILICATO BLANCO
Finish	Smooth matt
Specific weight	1,41± 0,05 kg/l
Viscosity	50 +/- 10 PO
Solids in volume	31± 1
Solids in weight	53± 1
VOC	Cat. c/BA 75/40 (2007/2010):0,00 g/l

Fecha de Alta

12-01-2021

Versión

9 - 21/04/2026

Aproximated performance by coat 6-8 m²/L

Dry to touch	(20°C HR:60%):2h
Dry to repaint	(20°C HR:60%):24h
Colours	White 103 Colors consult COF and ETERNA charts

SURFACE PREPAIRING

New surfaces

Apply on clean and dry surfaces.

On very porous surfaces regulate absorption with Primer Silicato.

On gypsum surfaces prime with Fixing emulsion.

Restoring and maintenance

1. Completely remove old paint as the silicate must be in contact with the mineral support for the petrification reaction (solidification).
2. On mouldy surfaces apply Monto Limpia Moho and remove remaining mould.
3. Glossy surfaces should be thinned out to ensure good adhesion.
4. Putty the surface defects with exterior filler (see product range 6 'SURFACE PREPARATION' for the corresponding product lines of powder fillers to make an adequate choice).
5. On surfaces with different textures (repairs and/or plasters) prime to obtain uniform absorption.

WAY OF USE

Application notes

It always must be applied on mineral supports of construction.

To shake the product until its perfect homogenization.

To print the support with PRIMER SILICATO diluted with water based on the porosity and state of the support.

To dilute the product with PRIMER SILICATO pure or mixed with water based on the porosity of the support.

You will put two or three coats of OVALDINE SILICATE in fine layers and without reviewing in humid.

Do not apply the product in inferior temperatures to 5°C nor humidity superior to 80%.

To avoid to paint on surfaces exposed to a strong sun.

In very absorbent supports to apply a coat of PRIMER SILICATO and 24 hours later 2-3 coats of OVALDINE SILICATO with 12-24 intervals hours.

In little absorbent supports to apply 2-3 coats of OVALDINE SILICATO.

Solvent for dilution and cleaning

Thinner: Primer Silicato. Cleaning: Water

Way of use	Aproximate dilution
Painting brush	5-20%
Roller	5-20%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
New work			
MAX	Primer Silicato diluido	Ovaldine Silicato diluido	Ovaldine Silicato
STD	Primer Silicato diluido		Ovaldine Silicato
Support weak			
MAX	Primer Silicato diluido	Ovaldine Silicato diluido	Ovaldine Silicato
STD	Primer Silicato diluido		Ovaldine Silicato
lime backset			
MAX	Primer Silicato diluido	Ovaldine Silicato diluido	Ovaldine Silicato

Fecha de Alta

12-01-2021

Versión

9 - 21/04/2026

STD	Primer Silicato diluido	Ovaldine Silicato
------------	-------------------------	-------------------

Old paintings

MAX	Eliminar + Primer Silicato diluido	Ovaldine Silicato diluido	Ovaldine Silicato
------------	------------------------------------	---------------------------	-------------------

STD	Eliminar + Primer Silicato diluido	Ovaldine Silicato
------------	------------------------------------	-------------------

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 12 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5º and 35ºC

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances.As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

12 L