

Fecha de Alta

09-09-2008

Versión

25 - 13/11/2025



FAMILY ANTIHUMEDAD E IMPERMEABILIZAC. / SISTEMAS TINTOMÉT
LINE IMPERMEABILIZACION VERTICAL

DESCRIPTION AND NATURE

Photoreticulable elastic and waterproof membrane for protection and decoration of façades and exterior walls. Isolates the façade from rainwater. Highly durable and resistant: sunlight (UV), extreme temperatures, rainwater, environmental dirt, microorganisms and mould, chalk, colour degradation, carbonation of concrete, paint ageing. Ideal for professional application. This product contributes to LEED®, BREEAM® and VERDE certifications.

USAGES

Outdoors/Indoors

Facades

Cement mortars

Porous brick

Concrete

PROPERTIES

Washability: Class 1 (according to Standard UNE-EN 13300)

With anti-mould additive

Opacity: Class 2 (according to Standard UNE-EN 13300)

Dry film thickness: E4 (between 200 and 400 microns, according to standard 1062-1) calculated for an average yield of approximately two coats for white (see Technical Characteristics). This information may vary depending on the colour chosen.

The product can be guaranteed for up to 12 years for white and 10 for COF and FE, see conditions

Water vapor permeability: V3 (breathable) (according to UNE-EN 1062-1 standard)

Gloss level: matt (according to 13300 standard, at 85° reflectance <10)

CE Marked (UNE-EN 1504-2)

Gloss: G3 (matt, according to the UNE-EN 1062-1 standard)

Permeability to liquid water: W3 (maximum impermeability) (according to UNE-EN 1062-1 standard)

Carbon dioxide permeability: C1 (anti-carbonation) (according to UNE-EN 1062-1)

Crack resistance certificate according to UNE-EN 1062-7 standard: A5 (23°C) and A4 (-10°C) for a yield of 0.75 l/m².

Absorbs micro-cracks up to 2 mm.



TECHNICAL CHARACTERISTICS

Referencia Color	OVALDINE ELASTIC BLANCO
Finish	Matt
Specific weight	1,31 ± 0,05 kg/l

Fecha de Alta

09-09-2008

Versión

25 - 13/11/2025

Viscosity	125 +/- 15 PO
Solids in volume	51 ± 1
Solids in weight	64 ± 1
VOC	Cat. c/BA 75/40 (2007/2010): 13,85 g/l
Aproximated performance by coat	3-4 m ² /L
Dry to touch	(20°C HR: 60%): 4-6h
Dry to repaint	(20°C HR: 60%): 24h
Colours	Bases: White 102, IN and TR Colours from the COF and FACHADAS ETERNA charts. TINTOMETRIC SYSTEMS.

SURFACE PREPARING

French norm DTU 42.1

New surfaces

Concrete and cement mortars:

1. Wait until completely set (minimum 30 days).
2. Use an abrasive jet to remove any potential efflorescence from the base.
3. Neutralise alkaline surfaces.
4. Sand down highly polished surfaces to open up the mortar.
5. Remove any strange products and/or residues from the base.
6. Use a suitable fixative to fix crumbly bases (Fijamont/Emulsion Fijadora).
7. Use outdoor plaster to fill any defects in the base (Plasmont Fibra Elástico/ Plasmont Exteriores or equivalent from the Montó range).

Porous bricks:

1. Remove any cracks, holes or irregularities with Plasmont Exterior or Montó equivalent.
2. Clean the surface before painting.
3. It is advisable to apply a primer before painting due to the porosity of the brick, thus avoiding wasting paint.

Restoring and maintenance

1. On painted surfaces, check that the paint is solid and well-adhered. Its condition must be assessed, in order to avoid possible incompatibilities. Dust and dirt must also be eliminated before repainting.
2. Completely remove old paint that is in poor condition or that is poorly-adhered.
3. Treat mouldy surfaces with Monto Limpia Moho.
4. Glossy surfaces should be thinned out to ensure good adhesion.
5. Putty the surface defects with exterior filler, being the Plasmont Fibra Elastic the most recommended (see the corresponding powder fillers and ready-mixed fillers in the SURFACE PREPARATION product range to make the right choice).

WAY OF USE

Application notes

- Do not apply the product at temperatures below 5°C or above 35°C or with imminent risk of rain.
- Do not apply in full sun or on excessively humid days.
- Shake the product until it is perfectly homogenised.
- For the first coat, dilute the product according to the porosity and state of the surface.
- Finish with one or more lightly diluted coats until the surface is completely covered.

Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	0-5%
Roller	0-5%
Air-less gun	0-10%
Air-mix gun	0-10%
Aerographic gun	0-10%
Low pressure turbo	0-10%

Fecha de Alta

09-09-2008

Versión

25 - 13/11/2025

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Old paintings in good condition			
MAX	Ovaldine Elastic diluido	Ovaldine Elastic	Ovaldine Elastic
STD	Ovaldine Elastic diluido		Ovaldine Elastic
Old paintings in bad state			
MAX	Eliminar + Fijamont, Emulsión Fijadora	Ovaldine Elastic	Ovaldine Elastic
STD	Eliminar + Ovaldine Elastic diluido		Ovaldine Elastic
Support with mould			
MAX	Limpiar + Monto Limpia Moho + Ovaldine Elastic diluido	Ovaldine Elastic	Ovaldine Elastic
STD	Limpiar + Monto Limpia Moho + Ovaldine Elastic diluido		Ovaldine Elastic
Support weak			
MAX	Fijamont, Emulsión Fijadora	Ovaldine Elastic	Ovaldine Elastic
STD	Ovaldine Elastic diluido		Ovaldine Elastic
Masonry mortar			
MAX	Fijamont, Emulsión Fijadora	Ovaldine Elastic	Ovaldine Elastic
STD	Ovaldine Elastic diluido		Ovaldine Elastic

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.


NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L, 12 L, 15 L



FAMILY LINE

DESCRIPTION AND NATURE

Photoreticulable elastic and waterproof membrane for protection and decoration of façades and exterior walls. Isolates the façade from rainwater. Highly durable and resistant: sunlight (UV), extreme temperatures, rainwater, environmental dirt, microorganisms and mould, chalk, colour degradation, carbonation of concrete, paint ageing. Ideal for professional application. This product contributes to LEED®, BREEAM® and VERDE certifications.

USAGES

PROPERTIES

Washability: Class 1 (according to Standard UNE-EN 13300)

With anti-mould additive

Opacity: Class 2 (according to Standard UNE-EN 13300)

Dry film thickness: E4 (between 200 and 400 microns, according to standard 1062-1) calculated for an average yield of approximately two coats for white (see Technical Characteristics). This information may vary depending on the colour chosen.

The product can be guaranteed for up to 12 years for white and 10 for COF and FE, see conditions

Water vapor permeability: V3 (breathable) (according to UNE-EN 1062-1 standard)

Gloss level: matt (according to 13300 standard, at 85° reflectance <10)

CE Marked (UNE-EN 1504-2)

Gloss: G3 (matt, according to the UNE-EN 1062-1 standard)

Permeability to liquid water: W3 (maximum impermeability) (according to UNE-EN 1062-1 standard)

Carbon dioxide permeability: C1 (anti-carbonation) (according to UNE-EN 1062-1)

Crack resistance certificate according to UNE-EN 1062-7 standard: A5 (23°C) and A4 (-10°C) for a yield of 0.75 l/m².

Absorbs micro-cracks up to 2 mm.



TECHNICAL CHARACTERISTICS

Referencia Color

Finish Matt

Specific weight 1,31 ± 0,05 kg/l

Viscosity 125 +/- 15 PO

Solids in volume 51 ± 1

Solids in weight 64 ± 1

Fecha de Alta

09-09-2008

Versión

25 - 13/11/2025

VOC	Cat. c/BA 75/40 (2007/2010): 13,85 g/l
Aproximated performance by coat	3-4 m ² /L

Dry to touch	(20°C HR: 60%): 4-6h
Dry to repaint	(20°C HR: 60%): 24h
Colours	Bases: White 102, IN and TR Colours from the COF and FACHADAS ETERNA charts. TINTOMETRIC SYSTEMS.

SURFACE PREPAIRING

French norm DTU 42.1

New surfaces

Concrete and cement mortars:

1. Wait until completely set (minimum 30 days).
2. Use an abrasive jet to remove any potential efflorescence from the base.
3. Neutralise alkaline surfaces.
4. Sand down highly polished surfaces to open up the mortar.
5. Remove any strange products and/or residues from the base.
6. Use a suitable fixative to fix crumbly bases (Fijamont/Emulsion Fijadora).
7. Use outdoor plaster to fill any defects in the base (Plasmont Fibra Elástico/ Plasmont Exteriores or equivalent from the Montó range).

Porous bricks:

1. Remove any cracks, holes or irregularities with Plasmont Exterior or Montó equivalent.
2. Clean the surface before painting.
3. It is advisable to apply a primer before painting due to the porosity of the brick, thus avoiding wasting paint.

Restoring and maintenance

1. On painted surfaces, check that the paint is solid and well-adhered. Its condition must be assessed, in order to avoid possible incompatibilities. Dust and dirt must also be eliminated before repainting.
2. Completely remove old paint that is in poor condition or that is poorly-adhered.
3. Treat mouldy surfaces with Monto Limpia Moho.
4. Glossy surfaces should be thinned out to ensure good adhesion.
5. Putty the surface defects with exterior filler, being the Plasmont Fibra Elastic the most recommended (see the corresponding powder fillers and ready-mixed fillers in the SURFACE PREPARATION product range to make the right choice).

WAY OF USE

Application notes

- Do not apply the product at temperatures below 5°C or above 35°C or with imminent risk of rain.
- Do not apply in full sun or on excessively humid days.
- Shake the product until it is perfectly homogenised.
- For the first coat, dilute the product according to the porosity and state of the surface.
- Finish with one or more lightly diluted coats until the surface is completely covered.

Solvent for dilution and cleaning

Water


Way of use	Aproximate dilution
Painting brush	0-5%
Roller	0-5%
Air-less gun	0-10%
Air-mix gun	0-10%
Aerographic gun	0-10%
Low pressure turbo	0-10%

Fecha de Alta

09-09-2008

Versión

25 - 13/11/2025



SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Old paintings in good condition			
MAX	Ovaldine Elastic diluido	Ovaldine Elastic	Ovaldine Elastic
STD	Ovaldine Elastic diluido		Ovaldine Elastic
Old paintings in bad state			
MAX	Eliminar + Fijamont, Emulsión Fijadora	Ovaldine Elastic	Ovaldine Elastic
STD	Eliminar + Ovaldine Elastic diluido		Ovaldine Elastic
Support with mould			
MAX	Limpiar + Monto Limpia Moho + Ovaldine Elastic diluido	Ovaldine Elastic	Ovaldine Elastic
STD	Limpiar + Monto Limpia Moho + Ovaldine Elastic diluido		Ovaldine Elastic
Support weak			
MAX	Fijamont, Emulsión Fijadora	Ovaldine Elastic	Ovaldine Elastic
STD	Ovaldine Elastic diluido		Ovaldine Elastic
Masonry mortar			
MAX	Fijamont, Emulsión Fijadora	Ovaldine Elastic	Ovaldine Elastic
STD	Ovaldine Elastic diluido		Ovaldine Elastic

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

PACKINGS

0.75 L, 4 L, 12 L, 15 L