

Fecha de Alta

26-02-2014

Versión

8 - 28/10/2024



FAMILY CREA

LINE FONDO

### DESCRIPTION AND NATURE

Acrylic and polyurethane water primer white. Penetrates, seals and covers the wood, closing its pores. To prepare new woods, before being painted with enamels. It allows to obtain good finishes. Equalizes absorptions and improves the appearance of the finish, increasing its performance. Sand very well, leaving smooth and smooth finishes.

### USAGES

Outdoors/Indoors

Cement

Plaster

Wood

### PROPERTIES

Penetration power

No sanding necessary for repainting. Non expensive maintenance

Good adhesion

Drying fast

Odourless when dry

Good applicability

### TECHNICAL CHARACTERISTICS

Referencia Color	CREA SELLADORA BLANCA
Finish	Satin
Specific weight	1,44± 0,05 kg/l
Viscosity	45 +/- 5 PO
Solids in volume	38± 1
Solids in weight	58± 1
VOC	Cat. d/BA 150/130 (2007/2010): 49,09 g/l
Aproximated performance by coat	7-10 m <sup>2</sup> /L

Dry to touch (20°C HR 60%): 1-2h

Dry to repaint (20°C HR 60%): 24h

Colours White

### SURFACE PREPAIRING

#### New surfaces

Cement, gypsum and its derivatives mortar:

- Wait until full setting (30 days minimum).
- Wait until they are very dry.
- The support must be free of foreign products and / or residues.
- Clean the support of possible efflorescence, as well as neutralize the alkaline surfaces.
- Putty with suitable putty the possible damage to the support.

New woods:

- Outdoors, protect the wood with Anticarcom as Klearxyl Di from attack by fungi and xylophagous insects.
- Apply on wood with a moisture content of less than 12%.

Fecha de Alta

26-02-2014

Versión

8 - 28/10/2024

- Sand and eliminate possible glue residues in the assemblies and machining failures.
- If the wood shows signs of aging, it must be previously sanded and dust removed by brushing or any other mechanical means.

### Restoring and maintenance

Wood and work (plaster, cement and derivatives) painted:

- On varnished woods, remove by pickling or by mechanical means, removing foreign products, poorly adhered areas or in poor condition. Lightly sand, remove dust from sanding and proceed as on new wood.
- Outdoors, protect the wood with Anticarcom as Klearxyl Di from attack by fungi and xylophagous insects.

## WAY OF USE

### Application notes

- Stir the product until it is perfectly homogenized.
- Apply following the rules marked in the attached application box.
- Do not apply the product at high temperatures, or on surfaces exposed to strong insolation.
- Maintain good ventilation conditions during the drying time.
- Do not apply with relative humidity higher than 80%.

### Solvent for dilution and cleaning

Water

Way of use	Aproximate dilution
Painting brush	0-10%
Roller	0-10%
Air-less gun	10-30%
Air-mix gun	10-30%

## SYSTEM

### Procedures depending of surface type

	Primer	Intermedium	Finish
<b>New work</b>			
<b>MAX</b>	CREA Selladora	CREA Selladora	CREA esmalte
<b>STD</b>	CREA Selladora		CREA esmalte
<b>New wood indoor/outdoor</b>			
<b>MAX</b>	Al exterior: Anticarcomas Klearxyl Di	CREA Selladora	CREA Esmalte Laca
<b>STD</b>	Al exterior: Anticarcomas Klearxyl Di	CREA Selladora	CREA Esmalte Laca

## SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

## NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

772343

# CREA SELLADORA



Fecha de Alta

26-02-2014

Versión

8 - 28/10/2024

## PACKINGS

0.5 L, 2.5 L