

BARNIZ PARQUET ACQUA MATE



FAMILY
LINE

TRATAMIENTOS DE LA MADERA / SISTEMAS TINTOMÉTRICOS

POLIURETANOS AL AGUA (SUELOS)

DESCRIPTION AND NATURE

Transparent matt water-based polyurethane varnish for varnishing woods in interiors when a good rub resistance and resistance to detergents is desired.

USAGES

Indoors
Wood
Parquet

PROPERTIES

Strongness
Transparence
Colourless
Good adhesion
Washability
smooth finish
useful like primer and finish
finishes with strong filling capability
colors as per wood chart with Montomix System
- Water-based
Odourless when dry

TECHNICAL CHARACTERISTICS

Referencia Color	BARNIZ PARQUET ACQUA MATE
Finish	Matt
Specific weight	1,02 ± 0,05 kg/l
Viscosity	50 +/- 5 SG
Solids in volume	28 ± 1
Solids in weight	30 ± 1
VOC	Cat. e/BA 150/130 (2007/2010):130,00 g/l
Aproximated performance by coat	12-16 m ² /L

Dry to touch	(20°C HR: 60%): 1-2 h. Total: 3 días
Dry to repaint	(20°C HR: 60%): 12-24h Can be walked on: 24 h
Colours	Base: Transparent

SURFACE PREPAIRING

New surfaces

New woods.

The surface must be free from foreign products and/or residues.

Apply to wood with a moisture content of less than 20%.

Apply to healthy, grease-free, dust-free and dry wood.

Sand and remove any remnants of glue from the joints and faults from machining.

If the wood shows signs of ageing it must first be sanded down and any dust removed using a plane or other mechanical device.

BARNIZ PARQUET ACQUA MATE

Restoring and maintenance

Varnished or painted woods:

- If the wood has been varnished with Montoxyl colour (code 1300): remove foreign products, remove any loose or peeling varnish, lightly sand, remove dust from sanding and proceed as on new woods.
- If the wood has been varnished with closed pore varnishes such as Barniz Sintético Universal Mate (code 1350), Satinado (code 1360), Brillante (code 1370) Barniz Velero (code 1380), Barniz Alta Montaña (code 1385) or similar, remove by stripping with Quitamont Universal (code 3510) or by mechanical means, and proceed as on new woods.
- If the wood has been varnished with cellulose or polyurethane varnishes, remove by stripping with Quitamont Universal (code 3510) or by mechanical means, and proceed as on new woods.
- If the wood has been enamelled with synthetic enamel (Montosintético (code 2020, code 2024), Marisma (code 2010, code 2014), Luxatín (code 2028) or similar), remove by stripping with Quitamont Universal (code 3510) or by mechanical means, and proceed as on new woods.

WAY OF USE

Application Notes

Stir the product until perfectly blended.

Apply on clean and dry substrates.

Apply following the recommended dilutions as described in the Application Systems section.

Sand before application to ensure good penetration and smoothing on the wood.

Do not apply the product at high temperatures or on surfaces exposed to strong sunlight.

Ensure good ventilation while product is drying.

Do not apply with relative humidity over 80%.

Solvent for dilution and cleaning

Water

Way of use

Painting brush

Roller

Air-less gun

Aerographic gun

Aproximate dilution

Fondo:10-20%. Acabado: 0-5%

Fondo: 10-20%. Acabado:0-5%

Fondo: 10-20%. Acabado: 5-20%

Fondo: 10-20%. Acabado: 5-20%

SYSTEM

Procedures depending of surface type

	Primer	Intermedium	Finish
Closed pore wood			
MAX	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate
STD	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate
wood indoor			
MAX	Montoxyl fondo	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate
STD	Decapar+Barniz Parquet Poliuretano al Agua Mate		Decapar+Barniz Parquet Poliuretano al Agua Mate
Parquet			
MAX	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate
STD	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate
Open pore varnished wood			
MAX	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate
STD	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate

BARNIZ PARQUET ACQUA MATE

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to establish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 4 L



FAMILY LINE

DESCRIPTION AND NATURE

Transparent matt water-based polyurethane varnish for varnishing woods in interiors when a good rub resistance and resistance to detergents is desired.

USAGES

PROPERTIES

Strongness
Transparence
Colourless
Good adhesion
Washability
smooth finish
useful like primer and finish
finishes with strong filling capability
colors as per wood chart with Montomix System
- Water-based
Odourless when dry

TECHNICAL CHARACTERISTICS

Referencia Color

Finish Matt

Specific weight 1,02 ± 0,05 kg/l

BARNIZ PARQUET ACQUA MATE

Viscosity	50 +/- 5 SG
Solids in volume	28± 1
Solids in weight	30± 1
VOC	Cat. e/BA 150/130 (2007/2010):130,00 g/l
Aproximated performance by coat	12-16 m²/L

Dry to touch	(20°C HR: 60%): 1-2 h. Total: 3 días
Dry to repaint	(20°C HR: 60%): 12-24h Can be walked on: 24 h
Colours	Base: Transparent

SURFACE PREPAIRING

New surfaces

New woods.

The surface must be free from foreign products and/or residues.

Apply to wood with a moisture content of less than 20%.

Apply to healthy, grease-free, dust-free and dry wood.

Sand and remove any remnants of glue from the joints and faults from machining.

If the wood shows signs of ageing it must first be sanded down and any dust removed using a plane or other mechanical device.

Restoring and maintenance

Varnished or painted woods:

- If the wood has been varnished with Montoxyl colour (code 1300): remove foreign products, remove any loose or peeling varnish, lightly sand, remove dust from sanding and proceed as on new woods.

- If the wood has been varnished with closed pore varnishes such as Barniz Sintético Universal Mate (code 1350), Satinado (code 1360), Brillante (code 1370) Barniz Velero (code 1380), Barniz Alta Montaña (code 1385) or similar, remove by stripping with Quitamont Universal (code 3510) or by mechanical means, and proceed as on new woods.

- If the wood has been varnished with cellulose or polyurethane varnishes, remove by stripping with Quitamont Universal (code 3510) or by mechanical means, and proceed as on new woods.

- If the wood has been enamelled with synthetic enamel (Montosintético (code 2020, code 2024), Marisma (code 2010, code 2014), Luxatín (code 2028) or similar), remove by stripping with Quitamont Universal (code 3510) or by mechanical means, and proceed as on new woods.

WAY OF USE

Application Notes

Stir the product until perfectly blended.

Apply on clean and dry substrates.

Apply following the recommended dilutions as described in the Application Systems section.

Sand before application to ensure good penetration and smoothing on the wood.

Do not apply the product at high temperatures or on surfaces exposed to strong sunlight.

Ensure good ventilation while product is drying.

Do not apply with relative humidity over 80%.

Solvent for dilution and cleaning

Water

Way of use

Painting brush

Roller

Air-less gun

Aerographic gun

Aproximate dilution

Fondo:10-20%. Acabado: 0-5%

Fondo: 10-20%. Acabado:0-5%

Fondo: 10-20%. Acabado: 5-20%

Fondo: 10-20%. Acabado: 5-20%

SYSTEM


Procedures depending of surface type

Primer

Intermedium

Finish

BARNIZ PARQUET ACQUA MATE



Closed pore wood

MAX	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate
STD	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate

wood indoor

MAX	Montoxyl fondo	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate
STD	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate	Decapar+Barniz Parquet Poliuretano al Agua Mate

Parquet

MAX	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate
STD	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate

Open pore varnished wood

MAX	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate
STD	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate	Barniz Parquet Poliuretano al Agua Mate

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in drain. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

PACKINGS

0.75 L, 4 L