

DISOLVENTE CLOROCAUCHO 1403



FAMILY DISOLVENTES

LINE DISOLVENTES

DESCRIPTION AND NATURE

Solvent of aromatic hydrocarbons.

USAGES

Regulation and control of the viscosity of application in the paintings where his use is recommended
Cleanliness of tools in the recommended products
Specific for dilution chlorinated rubber paint

PROPERTIES

Fast evaporation
Does not harms final product properties if the proportions are the adecuated
Allows a good fining with stirring surface

TECHNICAL CHARACTERISTICS

Referencia Color	DISOLVENTE CLOROCAUCHO 1403
Finish	Transparent
Specific weight	0,84± 0,05 kg/l
Solids in volume	0± 1
Solids in weight	0± 1
Aproximated performance by coat	Depending of product usage

SURFACE PREPAIRING

New surfaces

Proceed following the paint instructions in which this product is recommended.

Restoring and maintenance

Proceed following the paint instructions in which this product is recommended.

WAY OF USE

Application Notes

-As a viscosity regulator:
-Add on top of paint or varnish, in the proportion stated in the specifications sheet of the product to be diluted.
-Slowly stir the previous mix with a spatula until you get a smooth mixture.

-As a tool cleaning solvent:
-Clean tools immediately after use until all varnish and paint has completely disappeared.
-Then wash with soapy water and dry immediately after washing.

Solvent for dilution and cleaning

Way of use

Aproximate dilution

DISOLVENTE CLOROCAUCHO 1403

SYSTEM

Procedures depending of surface type

Primer**Intermedium****Finish**

SECURITY

Do not eat, neither drink, nor smoke during the application. In case of contact with eyes, wash abundantly with clean water. Keep away from children. Do not throw in darin. Keep product in dry area, under cover and temperature between 5 to 35°C. For further information, please check product safety sheet.

NOTE

Maximum recommended storage time : 24 months since its fabrication in its original packaging perfectly closed, stored indoors and at temperatures between 5° and 35°C

Information here indicated is based on our actual knowledge, laboratory testing and taking in count the practical use under specific circumstances. As it is impossible to stablish an adequate description for every nature and status of the supports to be painted, we are unable to warrant the absolute reproductibility in each specific use

PACKINGS

0.75 L, 1 L, 5 L, 25 L